

# APPLICATION UNDER UNITED STATES PATENT LAWS

Atty. Dkt. No. PW 284079  
(M#)

Invention: HALOGEN-FREE FLAME-RETARDANT COMPOSITION

Inventor (s): Pieter Arie VAN DER SPEK  
Martinus Louis Maria BOS  
William Adrianus Cornelis ROOVERS  
Marnix VAN GURP  
Henrica Norberta Alberta Maria MENTING



00909

Pillsbury Winthrop LLP

This is a:

- ☐ Provisional Application
- ☐ Regular Utility Application
- ☒ Continuing Application
- ☒ The contents of the parent are incorporated by reference
- ☐ PCT National Phase Application
- ☐ Design Application
- ☐ Reissue Application
- ☐ Plant Application
- ☐ Substitute Specification
- Sub. Spec Filed \_\_\_\_\_  
in App. No. \_\_\_\_\_ / \_\_\_\_\_
- ☐ Marked up Specification re  
Sub. Spec. filed \_\_\_\_\_  
In App. No. \_\_\_\_\_ / \_\_\_\_\_

## SPECIFICATION

5        HALOGEN-FREE FLAME-RETARDANT COMPOSITION

          The invention relates to a halogen-free, flame-retardant composition comprising at least an organic phosphorus compound (A) and  
10    melamine or a compound derived from melamine (B), or a melamine-phosphorus compound (AB).

          Such a composition is known from WO 99/02606, which describes polybutylene terephthalate (PBT) compositions that contain a  
15    halogen-free, flame-retardant composition consisting of resorcinol-bis-(diphenylphosphate) (RDP) or a trimethylolpropanol ester of methylphosphonic acid and melamine  
20    cyanurate or melam. Said publication also describes a polyamide-6 composition that contains a halogen-free, flame-retardant composition consisting of the trimethylolpropanol ester of methylphosphonic acid and melamine cyanurate or melam.

          The drawback of the composition  
25    according to the state of the art is that the polycondensate compositions in which the flame-retardant composition can be used, in particular polyamide and polyester compositions containing glass fibres, have flame-retardant properties that  
30    do not yet meet the highest requirements. In particular the after-burning time is generally too long, in many cases even longer than 30 seconds, as a result of which no V-O classification according to the UL-94 test of the Underwriter Laboratories  
35    can be obtained. It is hence desirable to shorten

0093527-112701

the after-burning time, i.e. the time for which a composition burns after the removal of the flame. The polycondensate compositions in which the flame-retardant composition according to the invention is used can consequently for example obtain a better UL-94 classification, or a polycondensate composition with flame-retardant properties, similar to the ones disclosed in WO 99/02606, can be obtained using a smaller amount of flame-retardant composition.

The inventors have now surprisingly found that the after-burning time of a polycondensate composition that contains the flame-retardant components (A)+(B) or (AB) according to the state of the art can be shortened if the flame-retardant composition also contains a polymer compound (C) comprising at least one type of olefine having 2-12 carbon atoms and 0.1-30 wt.% (relative to the weight of the polymer compound) of at least one compound containing acid, acid anhydride or epoxy groups.

Another part of the invention is a polycondensate composition containing the flame-retardant composition according to the invention.

An additional advantage of the polycondensate composition according to the invention is that the mechanical properties of the polycondensate composition according to the invention are not or not significantly lower than those of the polycondensate compositions according to the state of the art that do not contain component (C).


As component (C), the flame-retardant composition according to the invention contains a polymer compound comprising at least one olefine having 2-12 carbon atoms and 0.1-30 wt.% (relative

to the weight of the polymer compound) of at least one compound containing acid, acid hydride or epoxy groups. Suitable compounds are for example ethylene, propylene or ethylene-propylene

- 5 copolymers containing 0.1-30 wt.% (relative to the weight of the copolymer compound) of a comonomer containing acid, acid anhydride or epoxy groups. Said polymers may also contain comonomers that do not contain the aforementioned groups, for example
- 10 acrylic esters or vinyl acetate. Preferably the polymer compound contains 0.5-12 wt.% (relative to the weight of the polymer compound) of a compound containing acid, acid anhydride or epoxy groups. Examples of such compounds are acrylic acid,
- 15 methacrylic acid, maleic anhydride, glycidyl acrylate and glycidyl methacrylate.

In a preferred embodiment the polymer compound is a compound having a general chemical composition based on E, X and Y, with E standing

- 20 for an ethylene radical, X standing for a radical formed from the compound



where

$\text{R}^1$  = alkyl radical having 1-8 carbon atoms

$\text{R}^2$  = H,  $\text{CH}_3$  or  $\text{C}_2\text{H}_5$

- 30 and Y a radical formed from glycidyl (alkyl)acrylate; for example glycidyl (meth)acrylate.

Preferably the polymer compound based on E, X and Y contains 40-90 wt.% E, 1-40 wt.% X and 0.5-20 wt.% Y, the sum of the amounts being equal to 100 wt.%.

- The use of polymer compounds having a
- 5 chemical composition based on E, X and Y in concentrations of 1 - 20 wt.% in halogen-containing flame-retardant polyester compositions is known from EP-B1-174,343 (DuPont) for increasing the ductility of said polyester compositions,
- 10 especially at low temperatures.

- The polymer component (C) is commercially available, for example as an ethylene/acrylic ester/glycidyl methacrylate terpolymer (Lotader® AX, Elf Atochem),
- 15 ethylene/glycidyl methacrylate (Bondfast®, E with a mol. weight  $M_n = 120,000$ , Sumitomo), ethylene/methacrylic acid (Nucrel®, Dupont), propylene/maleic anhydride (Himont), propylene/acrylic acid (Polybond®, BP Chemical) and
- 20 ethylene/alfa-olefine copolymer modified with maleic anhydride (Tafmer®, Mitsui). Preferably, an ethylene/acrylic ester/glycidyl methacrylate terpolymer is chosen, more preferably an ethylene/methylmethacrylic ester/glycidyl
- 25 methacrylate terpolymer (Lotader® AX 8900, Elf Atochem, with a molar weight ( $M_n$ ) of approximately 90,000).

- In polyester compositions good results were obtained with an ethylene/methylmethacrylic
- 30 ester/glycidyl methacrylate terpolymer (Lotader® AX 8900). In polyamide compositions good results were obtained with an ethylene-propylene copolymer,

00990327 412701

modified with 0.5 wt.% maleic anhydride (Tafmer<sup>®</sup>, Mitsui).

- Suitable organic phosphorus compounds (component A) are for example organic phosphates, phosphites, phosphonates, phosphinates and phosphine oxides. Preferably, phosphates, phosphonates or phosphinates are chosen. Examples of such phosphorus compounds are described in for example the "Encyclopedia of Chemical Technology", Vol. 10, p. 396 ff. (1980). Many are commercially available, for example resorcinol-bis(diphenylphosphate) oligomer, under the trade name Fyrolflex<sup>®</sup> RDP from AKZO-Nobel, NL; cresyl-diphenylphosphate (CDP) under the trade name Kronitex<sup>®</sup> CDP from FMC, UK; trimethylolpropanol ester of methylphosphonic acid, under the trade name Antiblaze<sup>®</sup> 1045 from Albright & Wilson, USA; poly(pentaerythritol) phosphonate under the trade name Cyagard<sup>®</sup> RF 1041 from American Cyanamid, USA; Hostaflam<sup>®</sup> OP 910, a mixture of cyclic di- and triphosphonates from Clariant, Germany.

Preferably, a phosphorus compound with a low volatility is chosen as component (A).

- Suitable for use as the compound derived from melamine (component B) are for example melamine derivatives, melamine condensation products or mixtures thereof. In the context of this application a "melamine derivative" is understood to be melamine with one or more amine groups having been substituted with one or more alkyl, aryl, aralkyl or cycloalkyl groups, for example to be chosen from the group comprising methyl, ethyl, ethenyl, phenyl or toluyl. Examples of such melamine derivatives are N,N',N''-

0903027-112701

triphenylmelamine. Another example of a melamine derivative is melamine cyanurate. In the context of this application a "melamine condensation product" is understood to be a compound in which two or more melamine compounds are connected to one another, for example melam, melem, melon and higher oligomers and menthone, which can for example be obtained using the process described in WO 96/16948.

Preferably, melamine, melamine cyanurate, melamine phosphate, melam, melem or mixtures thereof are chosen as component (B).

Suitable for use as the melamine-phosphorus compound (AB) are compounds like melamine phosphates, for example melamine pyrophosphate and melamine polyphosphate.

The flame-retardant composition according to the invention is used in polycondensate compositions in concentrations between 1 and 50% (relative to the total weight of the polycondensate composition), preferably between 10 and 40%. The concentration can in principle be determined experimentally by a person skilled in the art. The ratio of components (A), (B), (AB) and (C) may also vary within a wide range. The concentration of organic phosphorus compound (component A) may vary within a wide range, for example between 0.5 and 20 wt.% (relative to the total weight of the polycondensate composition), preferably between 1 and 15 wt.%. The concentration of melamine or compound derived therefrom (component B) may vary within a wide range, for example between 2 and 25 wt.% (relative to the total weight of the polycondensate composition), preferably between 3 and 20 wt.%, most preferably

5

10

15

25

30



Elastomers", 2nd Ed., Chapter 8 (1996), Hanser Verlag, the relevant contents of which is regarded as mentioned here. Furthermore, also polyester blends are suitable, such as PET/PBT,

5 PBT/polycarbonate or PBT/rubber blends.

Examples of suitable polyamides are the aliphatic polyamides PA-6, PA-6,6, PA-9, PA-11, PA-4,6 and copolyamides thereof and semi-aromatic polyamides based on for example PA-6 or PA-6,6 and aromatic dicarboxylic acids and aliphatic diamines, for example isophthalic acid and terephthalic acid and hexanediamine, for example PA-6/6.T, PA-6,6/6,T, PA-6,6/6/6,T and PA-6,6/6,I/6,T. Preferably PA-6, PA-6,6 and PA-4,6 are chosen.

15 Furthermore, also polyamide blends are suitable.

The composition according to the invention can also be used in polycondensate compositions that contain other additives known to a person skilled in the art that are usually used in polycondensate compositions, without them essentially detracting anything from the invention, in particular pigments, processing aids, for example mould release agents, crystallisation accelerators, nucleating agents, softeners, UV and heat stabilisers, antioxidants and the like. Other substances that promote the flame-retardancy can optionally be added, too, for example carbon-forming substances such as polyphenylene ether and polycarbonate and substances that affect the dripping behaviour, for example fluoropolymers such as polytetrafluoroethylene.

In particular the polycondensate composition contains an inorganic filler or reinforcing agent. Suitable inorganic fillers or reinforcing agents are all the fillers known to a

35

0993357 112701

person skilled in the art, for example glass fibres, metal fibres, graphite fibres, aramide fibres, glass beads, aluminium silicates, asbestos, mica, clay, calcined clay and talk. Preferably,

5 glass fibres are chosen.

The polycondensate composition according to the invention can be obtained in a simple manner for example by means of melt-mixing. Preferably use is then made of an extruder fitted  
10 with means for dosing all the desired components to the extruder, either in the extruder's throat, or to the melt.

The invention will be further elucidated with reference to the following examples  
15 and comparative examples.

#### Examples

##### Examples I and II and Comparative Examples

20 A and B

A number of polyester compositions were prepared using the following components in varying concentrations:

Polycondensate: polybutylene terephthalate (PBT):

25 Arnite® PBT from DSM Engineering Plastics, the Netherlands.

Component A: Antiblaze® 1045 from Albright & Wilson, USA.

30 Component B: melamine cyanurate: Melapur® MC50 from DSM Melapur, the Netherlands.

Component C: Lotader® AX8900 from Elf Atochem, France. This component is a terpolymer of ethylene, methylmethacrylate (MMA, 24 weight%) and glycidyl methacrylate (GMA, 8 weight%) with a  
35 molecular weight  $M_n = 90,000$ .

Other additives:

- glass fibre: length 4-4.5 mm and diameter 10-14  $\mu\text{m}$
- release agent.

5 The compositions were prepared using a ZSK 30 twin-screw extruder.

The compositions were used to injection-mould specimens. They were subjected to the following

10 tests:

- flame retardancy according to UL94 at 1.6 mm after 48 hours at 23°C/50 % relative humidity (RH);
- determination of modulus of elasticity
- 15 according to ISO 527-1;
- determination of tensile stress at break according to ISO 527-1.

The results are summarised in Table 1.

09393927-712704  
10/2/2004

Table 1: Halogen-free polyester compositions. All the amounts are percents by weight, relative to the composition's total weight.

Example		A	I	B	II
Polyester	%	54.75	51.75	45	42
Component A	%	10	10	10	10
Component B	%	15	15	15	15
Component C	%	-	3	-	3
Other additives					
- glass fibre	%	20	20	30	30
- release agent	%	0.25	0.25	-	-
Flame retardancy					
UL94 at 1.6 mm		NC	V-0	V-1	V-0
after 48 hours at 23°C/50 % RH					
1st application of flame					
- average after-burning time	sec	17.6	2.4	2.4	1.4
- average time to dripping	sec	0	0	0	0
2nd application of flame					
- average after-burning time	sec	19	2.2	11.6	1.0
- average time to dripping	sec	26	0	0	0
Modulus of elasticity	MPa	6621	6466	9386	9123
Tensile stress at break	%	87	86	75	74

NC = no classification

V-0, V-1 and V-2 classifications according to UL-94

"average time to dripping" = the time from the application of the flame to the falling of the first drop.

From Table 1 it can be inferred that:

- the addition of component (C) to the composition according to the state of the art leads to a drastic shortening of the after-burning time, such that a V-O classification is obtained.
- the modulus of elasticity and the tensile stress at break are not essentially affected by the addition of component (C).

The flame retardancy of compositions I and A was also determined after 168 hours' conditioning at 70°C. The results are summarised in Table 2. A drastic shortening of the after-burning time was obtained under these conditions, too.

Table 2: Halogen-free polyester compositions

Example	Unit	A	I
Flame retardancy UL94 at 1.6 mm after 168 hours at 70°C		NC	V-1
1st application of flame			
- average after-burning time	sec	30.8	4.4
- average time to dripping	sec	40	0
2nd application of flame			
- average after-burning time	sec	28	12.0
- average time to dripping	sec	9.0	0

## Examples III-VI and Comparative Examples C-F

A number of polyester compositions were prepared using the following components in varying concentrations:

Polycondensate: polybutylene terephthalate (PBT):

Arnite® PBT from DSM Engineering Plastics, the Netherlands.

Component A:

AB : Antiblaze® 1045 from Albright & Wilson, USA.

NH : NH-1197 from Great Lakes, USA (cyclic ester of

pentaerythritol and phosphoric acid.

Component B: a mixture of melamine (2.5 weight%), melam (0.4 weight%), melem (79.1 weight%) and higher melamine homologues (18 weight%), obtained from DSM Melapur, the Netherlands.

- 5 Component C: Lotader<sup>®</sup> AX8900 from Elf Atochem, France. This component is a terpolymer of ethylene, methylmethacrylate (MMA, 24 weight%) and glycidyl methacrylate (GMA, 8 weight%) with a molecular weight  $M_n = 90,000$ .

10 Other additives:

- glass fibre: length 4-4.5 mm and diameter 10-14  $\mu\text{m}$ .

The compositions were prepared using a ZSK 30 twin-screw extruder.

- 15 The compositions were used to injection-mould specimens. They were subjected to the following tests:

- flame retardancy according to UL94 at 1.6 mm after 48 hours at 23°C/50 % relative humidity (RH);

- 20 The results are summarised in Table 3. From these results it is apparent that the compositions comprising Component C have a shorter after-burning time than the compositions without Component C. Also, the amount of Component B can be lowered in the presence of Component C without imparting the after-burning time of the composition.
- 25

Table 3: Halogen-free polyester compositions. All the amounts are percents by weight, relative to the composition's total weight.

Example	C	III	D	IV	E	V	F	VI
Polyester	%	45	48	45	45.6	43.6	45	42
Component A	%	10	7	7	6.4	6.4	AB:4 NH:4	AB:4 NH:4
Component B	%	15	15	15	18	18	17	17
Component C	%	-	-	3	-	2	-	3
Other additives								
- glass fibre	%	30	30	30	30	30	30	30
1st application of flame								
- av. after-burning time	Sec	1	10.6	2.0	10.6	3.0	1.0	2.0
2nd application of flame								
- av. after-burning time	Sec	1	6.8	1.0	2.8	1.0	3.0	2.0

Example VII and Comparative Example G

Polyamide compositions were prepared using the following components in varying concentrations:

- 5 Polycondensate: polyamide-6: Akulon® PA-6 from DSM Engineering Plastics, the Netherlands;  
Component A: P compound: Antiblaze® 1045 from Albright & Wilson, USA;  
Component B: melamine cyanurate: Melapur® MC50 from DSM Melapur, the Netherlands;
- 10 Component C: Tafmer® MP0610 from Mitsui, Japan  
Other additives:  
- glass fibre: length 4-4.5 mm, diameter 10-14 µm.
- 15 The compositions were prepared using a ZSK 30 twin-screw extruder.

Table 3: Halogen-free polyamide compositions

Example	Unit	G	VII
Polyamide-6	%	45.00	43
Component A	%	10	10
Component B	%	15	15
Component C	%	-	2
Other additives			
- glass fibre	%	30	30
Flame retardancy			
UL94 at 1.6 mm		V-2	V-0
after 48 h at 23°C/50 % RH			
1st application of flame			
- after-burning time	sec	1.0	1.0
- time to dripping	sec	0	0
2nd application of flame			
- after-burning time	sec	13.0	4.6
- time to dripping	sec	21.8	0
modulus of elasticity	MPa	10359	10079
tensile stress at break	%	154.7	141.9